



# TECHNICAL PAINT SERVICES

## A79 ZINC PHOSPHATE COLOURED FINISH

### **Features:**

A high quality single pack, fast drying, anti-corrosive Zinc Phosphate Self-Priming Finish suitable for direct application to ferrous metals. A79 may be over-coated with itself to create a sheen finish. A two coat system is recommended. It may also be applied to aluminium, galvanised or alloys after suitable priming (see below).

### **Availability:**

Supplied in BS4800 and RAL colours, in 5 Litre as standard, some colours are subject to minimum orders. Please note our products are made to order and it may take 7-10 days before shipping. This product is available at a discounted price in 25 Litre containers subject to a minimum order of 100 Litres.

### **Volume Solids:**

40% ± 3% (may vary with colour).

### **Preparation:**

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease. All rust should be pre-treated with Fertan Rust Treatment before the application of either A79 Finish or UP89/25 Primer. Aluminium, alloys or galvanised surfaces should be primed with UP89/25 Two Pack Etching Primer (see data sheet for application), prior to application of A79 Finish.

### **Application:**

It is recommended this product is applied by airless spray; small areas maybe brushed. Thin up to 10% by volume with UTR112 Universal Synthetic Thinners to achieve a spraying viscosity of 25 - 30 seconds BSB4 Cup @ 20°C.

### **Coverage:**

Approximately 25-35 sq. metres per 5 Litres @ 75 microns dry film thickness depending on surface profile.

### **Drying:**

Touch dry: 20 minutes @ 20°C.  
Firm dry: 1 hour @ 20°C.  
Recoatible: 3-4 hours @ 20°C.

**Health & Safety:** Please see MSDS sheet **10019**.

**Note:** For internal work, maximum ventilation is required. To assist drying if the air flow is insufficient, fans or other mechanical methods of circulating air should be adopted. Precautions must be taken to prevent operators from inhaling the vapours during application.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control. See Standard Conditions of Sale.

The majority of our products are for professional and trade/contractor use only and are not intended for DIY application. Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

A79 11 15

## FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.

27 SOUTHCOLE ROAD BOURNEMOUTH BH1 3SH Tel 01202 295 570 Fax 0845 230 1255  
Email enquiries@technicalpaintservices.co.uk www.technicalpaintservices.co.uk

Technical Paint Services is the trading name of Neatcross Ltd. Registered Office as above. Company No: 1570359.