



TECHNICAL PAINT SERVICES

AP79 UNIVERSAL PRIMER

Features:

A high quality, fast drying, anti-corrosive Synthetic Primer suitable for direct application to ferrous metals and wood. AP79 Universal Primer may be over-coated with Cellulose, Single and Two-Pack paint systems and can be forced dried or stoved for up to 30 minutes @ 120°C.

Availability:

Red Oxide and Grey in 5 Litre containers. Other colours made to order, subject to minimum orders. A cheaper Contract Grade, APG79 is also available, minimum 25 Litres. Please note our products are made to order and it may take 5-7 days before shipping.

Volume Solids:

55% ± 3% (BS 3900 Part A10).

Preparation:

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease. Aluminium, alloys or galvanised surfaces should be treated with UP89/25 Two Pack Etching Primer prior to application of AP79.

Application:

By brush, roller or conventional spray. Thin up to 25% by volume with UTR112 Universal Synthetic Thinners to achieve a spraying viscosity of 25 - 30 seconds BSB4 cup @ 20°C.

Coverage:

Approximately 40 - 50 sq metres per 5 Litres @ 25 microns dry film thickness.

Drying:

Touch dry:	15 - 20 minutes @ 20°C.
Hard dry:	30 minutes - 1 hour @ 20°C.
Recoatable:	1 hour @ 20°C.

Health & Safety: Please see MSDS sheet **10019**.

Note: For internal work, maximum ventilation is required. To assist drying if the air flow is insufficient, fans or other mechanical methods of circulating air should be adopted. Precautions must be taken to prevent operators from inhaling the vapours during application.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control. See Standard Conditions of Sale.

The majority of our products are for professional and trade/contractor use only and are not intended for DIY application. Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

AP79 03 15 Red & Grey

FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.

27 SOUTHCOTE ROAD BOURNEMOUTH BH1 3SH Tel 01202 295 570 Fax 0845 230 1255
Email enquiries@technicalpaintservices.co.uk www.technicalpaintservices.co.uk

Technical Paint Services is the trading name of Neatcross Ltd. Registered Office as above. Company No: 1570359.