HP45/20/4 MEDIUM TEMPERATURE ANTI-CORROSIVE RED OXIDE PRIMER

Features:

A specially formulated primer, resistant to temperatures up to 350°C. Suitable for interior or exterior use, this product is ideal for application to flues, boilers and ovens. Can be over-coated with Technical Paint Services heat resistant finishes.

Availability:

5, 2.5 and 1 Litre containers.

Volume Solids:

 $55\% \pm 3\%$ (BS 3900 Part A10).

Preparation:

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease. It is suitable for direct application to steel surfaces.

Application:

Do not apply to heated surfaces, cool before applying by brush or conventional spray. Thin up to 20% by volume using UTR112 Universal Synthetic Thinners to achieve a suitable spraying viscosity.

Coverage:

Approximately 30 - 40 sq metres per 5 Litres @ 25 microns dry film thickness.

Drying:

Touch dry: 30 minutes @ 20°C. Hard dry & recoatable: 4 hours @ 20°C.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.

See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.