



TECHNICAL PAINT SERVICES

R34 CHLORINATED RUBBER FLOOR FINISH

Features:

A fast drying, single pack floor finish which has excellent resistance to a wide range of chemicals, including acids, alkalis, inorganic salts, mineral oil and water. Ideally suited for application to “green” concrete floors as R34 can be applied when concrete is 3 - 4 weeks old. This paint should not be applied over PVA sealer, latex self leveling compound or power floated concrete. Please contact our Technical Department.

Availability:

BS4800 colour range made to order in minimum of 5 Litre containers. R35 Chlorinated Rubber Floor Finish Non-Slip is also available. Please note our products are made to order and it may take 5-7 days before shipping.

Volume Solids:

51% ± 3% (BS 3900 Part A10).

Preparation:

The surface should be clean, dry and free from dust and grease.

Application:

Brush, roller, conventional or airless spray. Supplied ready for use for brushing. Thin up to 25% by volume with UTR112 Universal Synthetic Thinners to achieve a suitable spraying viscosity. R34 may be applied over WBP1020 Two Pack Epoxy Primer.

Coverage:

40 sq metres per 5 Litres @ 25 microns dry film thickness.

Drying:

Touch dry: 1 hour @ 20°C.
 3 hours @ 10°C.
Recoatable: 8 hours @ 20°C.
 12 hours @ 10°C.

Light foot traffic after 24 hours. Full use after 3-5days.

Health & Safety: Please see MSDS sheet **10019**.

Note: For internal work, maximum ventilation is required. To assist drying if the air flow is insufficient, fans or other mechanical methods of circulating air should be adopted. Precautions must be taken to prevent operators from inhaling the vapours during application.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control. See Standard Conditions of Sale.

The majority of our products are for professional and trade/contractor use only and are not intended for DIY application. Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

R34 04 14

FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.