



TECHNICAL PAINT SERVICES

ACRYLIC SWIMMING POOL PAINT WB148

Features:

Water based 100% pure Acrylic Swimming Pool Paint, suitable for application to all types of porous substrates and other pool coatings, but not suitable for application over two pack epoxies. Exhibiting excellent water resistance and also suitable as a coating for inside concrete ponds. If you wish to paint a newly rendered or concreted surface that is less than 8 - 10 weeks old, it is recommended that you use our Chlorinated Rubber Swimming Pool Paint A148, which can be applied after just 4 weeks.

Availability:

5 Litres minimum. In the BS4800 colour range, plus Black and White. A choice of fine or medium texture non-slip finish is also available. Limited RAL colours to order. Please note our products are made to order and it may take 5-7 days before shipping.

Volume Solids:

45% ± 3% (BS 3900 Part A10).

Preparation:

The surface should be thoroughly clean, dry and free from dust and grease. Please see our Swimming Pool Guide for surface preparation guidance to application. This can be downloaded from our web site. Please remember the key to a successful finish is the preparation given to the surface to be coated. Where a pool liner is being removed and you wish to paint the inner surface, we strongly recommend you call our Technical Team before you commence. Where a badly degraded, old or unstable surface exists, it must be stripped prior to application.

Application:

Brush, roller, conventional or airless spray. Supplied ready for use for brushing or rolling. On all new and stripped surfaces, a thinned first coat should be applied using clean tap water thinning up to 15% by volume. It is then recommended that a further two full coats be applied to the surface, allowing 4 - 6 hours drying between coats. After the final coat is applied, the surfaces should be left for 5 days to fully dry. If there is rain during that time, remove any standing water after the rain has stopped. Use a sponge and leaf blower to dry the pool. If the rain lasts more than an hour or two, add a day to the cure time.

Coverage:

Approximately 40 - 50 sq metres per 5 Litres, depending on porosity of substrate.

Drying:

Touch dry: 30 minutes @ 20°C.
Hard dry & recoatable: 4-6 hours @ 20°C.
Fully dry: Minimum 5 days.

Health & Safety: Please see MSDS sheet 100C3.

Note: For internal work, maximum ventilation is required. To assist drying if the air flow is insufficient, fans or other mechanical methods of circulating air should be adopted. Precautions must be taken to prevent operators from inhaling the vapours during application.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control. See Standard Conditions of Sale.

The majority of our products are for professional and trade/contractor use only and are not intended for DIY application. Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

WB148 10 14

FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.

27 SOUTHCOLE ROAD BOURNEMOUTH BH1 3SH Tel 01202 295 570 Fax 0845 230 1255
Email enquiries@technicalpaintservices.co.uk www.technicalpaintservices.co.uk

Technical Paint Services is the trading name of Neatcross Ltd. Registered Office as above. Company No: 1570359.