



TECHNICAL PAINT SERVICES

A136 MICACEOUS IRON OXIDE PHENOLIC TUNG

Features:

A high performance, anti-corrosive, protective finish for iron and steel. When used as part of a three coat system comprising AP114 Two Pack Epoxy Primer, AP136 M.I.O. Phenolic Tung Undercoat and A136 M.I.O. Phenolic Tung Finish, it provides an extremely tough, durable finish for structural steelwork and sheet steel cladding.

Availability:

Light Grey and Dark Grey in 5 Litre containers. Other colours made on request, minimum 25 Litre lots. Please note our products are made to order and it may take 5-7 days before shipping.

Volume Solids:

55% ± 3% (BS 3900 Part A10).

Preparation:

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease. Apply over primer and undercoat systems as outlined above.

Application:

By brush or airless spray. Supplied ready for use for brushing. Thin up to 5% by volume with White Spirit for airless spray. Avoid excessively thick coats or rapid over-coating, as this will result in soft finishes.

Coverage:

Approximately 45 - 50 sq metres per 5 Litres @ 50 microns dry film thickness.

Drying:

Hard dry & recoatable: 16 hours @ 20°C.

Health & Safety: Please see MSDS sheet **100D4**.

Note: For internal work, maximum ventilation is required. To assist drying if the air flow is insufficient, fans or other mechanical methods of circulating air should be adopted. Precautions must be taken to prevent operators from inhaling the vapours during application.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control. See Standard Conditions of Sale.

The majority of our products are for professional and trade/contractor use only and are not intended for DIY application. Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

A13615 04 14

FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.

27 SOUTHCOTE ROAD BOURNEMOUTH BH1 3SH Tel 01202 295 570 Fax 0845 230 1255
Email enquiries@technicalpaintservices.co.uk www.technicalpaintservices.co.uk

Technical Paint Services is the trading name of Neatcross Ltd. Registered Office as above. Company No: 1570359.