R11 HIGH BUILD CHLORINATED RUBBER PAINT

Features:

A high build, single pack system resistant to a wide range of chemicals, including acids, alkalis, oxidising agents, inorganic salts, moist gases and mineral oil. Ideal for use as an undercoat for R10 Chlorinated Rubber Paint where a thick film is required for severe conditions. In less severe environments it can be used as a topcoat for chemical storage tanks, bridges, marine equipment, sewage tanks etc.

Availability:

BS4800 colour range made to order in 5 Litre containers only. R12 Micaceous Iron Oxide type is also available. Please note our products are made to order and it may take 5-7 days before shipping.

Volume Solids:

 $62\% \pm 3\%$ (BS 3900 Part A10).

Preparation:

The surface should be clean, dry and free from corrosion, dust and grease. R11 may be applied over RP10 Chlorinated Rubber Primer, AP79 Universal Primer, AP83/65 Zinc Rich Galvanic Primer, UP89 Two Pack Etching Primer or WBP1020 Two Pack Epoxy Primer.

Application:

Brush, roller or airless spray. Supplied ready for use for brushing. Thin up to 20% by volume with UTR112 Universal Synthetic Thinners to achieve a spraying viscosity of 25 - 30 seconds BSB4 cup @ 20°C.

Coverage

30 sq metres per 5 Litres, giving a dry film thickness of 60 - 70 microns.

Drying:

Touch dry: 30 - 40 minutes @ 20°C.

3 hours @ 10°C.

Recoatable: 8 hours @ 20°C.

12 hours @ 10°C.

Health & Safety: Please see MSDS sheet 10019.

Note: For internal work, maximum ventilation is required. To assist drying if the air flow is insufficient, fans or other mechanical methods of circulating air should be adopted. Precautions must be taken to prevent operators from inhaling the vapours during application.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control. See Standard Conditions of Sale.

The majority of our products are for professional and trade/contractor use only and are not intended for DIY application. Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

R11 04 14

FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.